

COMPOSITION AND MATERIALS:

(For complete instructions refer to each product's Technical Data)

SEALER COAT: AQUASEAL ME12

AQUASEAL ME12 is a clear flat, water base, penetrating Silane/Siloxane water repellent. It must be applied to the entire exterior elevation (unless the surface is painted and sealed for the full elevation) to maintain the integrity of the natural (unpainted) surfaces and to protect the **PERMASHIELD PREMIUM** application. **AQUASEAL ME12** protects against water seepage and allows for a more consistent application of the Graffiti Control System.

- A. **AQUASEAL ME12** should be applied in a uniform manner. Each application coat consists of a light fog spray coat that wets the entire surface and breaks the surface tension. The fog spray coat must be followed immediately with a flood coat to achieve maximum penetration. Allow the material to run down 10 to 12 inches. Back rolling the run downs isn't required but will maximize the seal. A low pressure spray gun with a tip size of 0.035 inch is recommended. Allow 24 hours of dry time prior to applying **PERMASHIELD BASE**.
- B. The estimated coverage rate is approximately 50-80 square feet per gallon over porous concrete including mammoth block, standard block, split face block, old masonry brick, etc. Refer to our Technical Data Sheet for additional spread rates and information.
- C. Coverage rates may vary considerably due to the porosity of the substrate. Always test and obtain approval from the project architect and/or building owner prior to starting the job.

NOTE: For chalky concrete, stucco, plaster, and tilt-ups, substitute **AQUASEAL ME12** with **AQUABOND**. **AQUABOND** positive waterproofing cohesively binds chalky surfaces and is available in a clear finish. For detailed information and application instructions, please refer to the technical data pages.

BASE COAT: PERMASHIELD BASE

PERMASHIELD BASE is a single component, water based aliphatic polyurethane designed to provide a pin-hole free surface for the **PERMASHIELD PREMIUM**. It can be applied to porous substrates such as split-face block, mammoth block, CMU, stucco, masonry and other permeable substrates.

PERMASHIELD BASE is available in both clear base and white base and can be tinted to any color.

Item No. 6100: Clear Base Item No. 6150: White Base

- A. For unpainted surfaces, apply two coats of **PERMASHIELD BASE** to create a pinhole free surface. Do not proceed to the **PREMIUM** topcoat if there are pinholes present after applying the **PERMASHIELD BASE**.
- B. For sound previously painted surfaces, apply one or two coats of **PERMASHIELD BASE** to maintain the natural look of the surface.

- C. **PERMASHIELD BASE** can be applied using a good quality roller, brush or airless sprayer with a tip size of .013-.017 inch. The estimated coverage rate is approximately 200 - 250 square feet per gallon, resulting in 2-3 dry mils thickness per coat (4-6 dry mils for 2 coats).
- D. Allow 1-3 hours dry time prior to applying the second coat. Apply the second coat after the milky-ness of the first coat clears. Allow 24 hours dry time before applying **PERMASHIELD PREMIUM** top coat.
- E. Do not proceed to the **PERMASHIELD PREMIUM** topcoat until the surface is pinhole free.

TOP COAT: PERMASHIELD PREMIUM

PERMASHIELD PREMIUM is a clear 2-component, water base, aliphatic polyurethane top coat available in clear matte or clear gloss. **PERMASHIELD PREMIUM** must be applied to a pin-hole free surface.

MIXING INSTRUCTIONS:

- A. **PERMASHIELD PREMIUM** clear gloss or matte finish is a water based, 2-component aliphatic polyurethane top coat.
- B. Stir Part A only before blending. Do not stir Part B.
- C. Add Part B to Part A (already stirred); use an electric mixer to blend the two parts. Scrape all the Part B out of the can. Mix for 2 to 3 minutes. No partial mixing.
- D. The pot life of the mixture is 1 to 2 hours, depending on temperature.
- E. Discard the unused mixture after 2 hours.
- F. Do not blend new mixture with the old.

APPLICATION PRECAUTIONS:

- **CAUTION!** Do not apply thicker than 6 wet mils thickness to avoid micro blistering.
- In all applications, we require doing a test section to determine the compatibility, adhesion, spread rates and appearance. All surfaces must be tested and approved by architect or project owner prior to doing the complete project.
- Do not apply to surfaces containing 15% or higher moisture content or hydrostatic pressure.
- Air and surface temperatures must be between 50°F. and 90°F during application.
- Sprinklers that come into contact with the application must be turned off for at least two days prior to and two days after application to maximize the life of the application. Redirect the sprinklers so they do not make contact with the coatings.
- Do not apply in windy conditions.
- Do not apply to surfaces displaying a pH over 8.
- Protect the surrounding areas from overspray.
- Do not apply if rain is imminent within 48 hours.
- For application over previously painted surfaces, allow the paint to fully cure (at least 7-14 days; consult the paint's technical data sheet for exact cure time) before applying **PERMASHIELD PREMIUM**. Refer to "Caution" section on page 4.

APPLICATION

A continuous application will ensure a smooth and level coat with no lines or streaks to disfigure the surface. The application should not be stopped part of the way across an area and completed later.

PERMASHIELD PREMIUM should be applied at an approximate rate of 200-250 square feet per mixed gallon, yielding 3-4 dry mils per coat. Two coats are required.

PERMASHIELD PREMIUM can be applied by brush, roller or an airless sprayer with a tip size of .013 to .017 inches. The spray tip should be new and not stretched from previous uses. Make sure to follow the spray application with an immediate back roll.

Allow 4-6 hours drying time (do not exceed 12 hours) prior to applying the second coat. After application, allow the **PERMASHIELD PREMIUM** to cure for a minimum of 48 hours in dry conditions. Allow up to five days for full cure and hardness (depending on temperature) before exposing the system to markers and spray paint tagging.

PERMASHIELD PREMIUM can be applied directly to properly prepared surfaces such as primed metal and previously painted water based epoxies and urethanes. Abrade and clean the previous water base coating to provide tooth for the **PERMASHIELD PREMIUM**. Always conduct a test patch to ensure the proper adhesion.

Note: For applications over horizontal surfaces, wood, steel or metal contact Monopole, Inc. for more information.

CLEAN-UP:

Do not allow **PERMASHIELD BASE** and **PERMASHIELD PREMIUM** to dry in the spray equipment. Empty spray equipment and wash with water while the material is fresh. Keep in mind the 1-2 hour pot life of **PERMASHIELD PREMIUM** (the mixture will thicken). Schedule your mixing, application and clean up accordingly.

MURALS

PERMASHIELD PREMIUM can be applied over murals that are not classified as "permanent" and won't be touched up in the future. It is not suitable for application over painted murals classified by the Federal, State, or City Counties as "Artwork" which is subject to continuing redesign and refinish. It would be extremely difficult to remove this permanent/non reversible system in order to redo the murals.

LIMITATIONS:

PERMASHIELD PREMIUM does not seal inaccessible areas. It will not bridge cracks, fill large pores or compensate for flawed construction. Exposed walls must be capped and the backside of parapet walls must be sealed, flashing must be in place and weep holes and drains installed and functioning (where applicable).

GRAFFITI REMOVAL

REMOVER: CITRUS CLEAN SUPER

CITRUS CLEAN SUPER (#9800) is a water-miscible, easy to use, concentrated cleaner/remover. It is designed to remove and clean graffiti from surfaces that are protected with **PERMASHIELD PREMIUM Graffiti Control System**.

- A. Spray **CITRUS CLEAN SUPER** directly on the graffiti and allow 2 minutes of dwell time. Do not allow the cleaner to dry. Gently agitate with a stiff bristle nylon brush or nylon scour pad working the cleaner into the graffiti. Spray more cleaning solution to maintain a wet surface and to remove the dissolved graffiti. When the graffiti removal is complete and all graffiti is dissolved, flush the surface thoroughly with water to removal all residues. Do not flush the surface with water if the graffiti removal is incomplete. If the removal is incomplete and exposed to water, allow the water on the surface to fully dry for 1-2 hours (wipe the surface dry) before repeating the above steps.
- B. **CAUTION!** Do not allow **CITRUS CLEAN SUPER** or graffiti run downs (from cleaning the surface) to dry on the surface.
- C. **CITRUS CLEAN SUPER** is the required graffiti remover for **PERMASHIELD PREMIUM**. Do not use solvents or other chemicals such as MEK, lacquer thinners, etc.

WARRANTY:

Monopole Inc. warrants the **PERMASHIELD PREMIUM Graffiti Control System** for a period of 10 years as long as the substrate, application, and removal methods meet the guidelines. For the duration of the 10 year warranty no additional graffiti coatings will need to be applied. After each graffiti removal the warranty protects against yellowing, shadowing, ghosting, or chemical staining.

PERMASHIELD PREMIUM warranties are available on an individual job basis and must be approved prior to application. Contact Monopole's service department for further information. The warranty is only valid using **CITRUS CLEAN SUPER** as the remover.

WARRANTY REQUIREMENTS:

1. The purchaser must obtain a written specification letter from Monopole, Inc. prior to the application outlining the application, substrate, and removal methods.
2. The applicator shall warrant that they have applied the materials in compliance with Monopole Inc's written specifications and instructions upon application completion.
3. Attempts to remove graffiti defacing from a surface treated with **PERMASHIELD PREMIUM Graffiti Control System** must be performed according to the exact procedure explained on the technical bulletin and specification letter. No other chemical cleaners should be used except **CITRUS CLEAN SUPER** or approved equal by Monopole, Inc.

SAFETY & STORAGE:

Contact with eyes can create irritation. If in contact, flush the eye area with water for 10 minutes. If swallowed, do not induce vomiting and consult a physician. Use in well ventilated areas. Keep the container tightly closed when not in use. Store in dry, cool areas in temperatures between 55°F - 95°F. Consult MSDS for additional details.

PACKAGING:

PERMASHIELD PREMIUM is available in a 96 OZ Kit or a 3-Gallon Kit.

The volume mixing ratio is 2:1 (2 Parts A to 1 Part B).

Caution! Painted & Stucco Surfaces

PERMASHIELD graffiti resistant coatings are clear non-yellowing products and may be used over acrylic painted or unpainted surfaces. However on rare occasion certain pigmented paint and color integrated stucco formulations (powdery stucco included) contain a biocide that may create yellowing when top coated with a clear graffiti resistant coating. This rare phenomena of ambering occurs on ~1 out of 40 painted/color integrated stucco jobs. Yellowing can be severe and normally appears within 3-7 days of direct sunlight exposure, particularly during hot weather. This can be addressed on the test patch.

If ambering has occurred (or to minimize the chance of it occurring), allow the fresh paint and/or stucco to fully cure (1-2 weeks minimum for paint and 28 days for fresh stucco), prior to applying a clear graffiti resistant coating. Consult the manufacturer of the paint coating and/or stucco to determine the full curing time.

To ensure proper results, Monopole requires applying a small test patch on each of the different paints and stucco surfaces prior to product application. It is very important that these test patches receive direct UV exposure. Allow the test areas 4-7 days of dry time (in direct sunlight) and then check for ambering prior to proceeding with the job. Monopole is not responsible for yellowing, whitening, discoloration, or any other consequential damages associated with the application of our **PERMASHIELD GRAFFITI RESISTANT** coatings. The end user shall determine the product's suitability and assumes all risks and liabilities.

TABLE 1

| Product Qualifications / Approvals | |
|--|------------------------|
| Cal Green | Yes |
| OTC (Industrial Maintenance) | Yes |
| SCAQMD (Industrial Maintenance) | Yes |
| CARB (Industrial Maintenance) | Yes |
| LEED (New Construction) | Yes |
| LEED (New Schools / CHPS) | Yes |
| LAUSD Exclusive Specification | Yes |
| Los Angeles RR | RR25080-T |
| MPI Approved Product | #105 |
| CALTRANS | 08-09-017 |
| CALTRANS Office of Health and Safety Services | Yes |
| Nevada DOT (QPL Approved per SPEC. 502.02.05a) | Yes |
| Texas Type II Permanent, Water Cleanable Classification Anti-Graffiti Coatings | Complies with DMS-8111 |

TABLE 2

| CHEMICAL RESISTANCE: (ASTM D1308) | |
|-----------------------------------|--------------------------|
| MEK double rubs..... | 300+ cycles (Level 5) |
| Skydrol | No effect after 7 days |
| Brake Fluid | No effect after 7 days |
| Gasoline | No effect after 7 days |
| Motor Oil..... | No effect after 7 days |
| Betadine | No effect after 24 hours |
| 50% NaOH | No effect after 24 hours |
| 14% NH4OH | No effect after 24 hours |
| 10% Acetic Acid | No effect after 24 hours |
| 10% H2SO4..... | No effect after 24 hours |
| 10% HCL | No effect after 24 hours |
| 10% Bleach | No effect after 24 hours |
| DI Water..... | No effect after 24 hours |
| IPA | No effect after 4 hours |
| Toluene | No effect after 4 hours |
| Acid Rain | No effect after 4 hours |

**TABLE 3
GRAFFITI RESISTANCE: (ASTM D6578)**

| Marking Substance: | Recommended Cleaners: | Cleanability Levels: |
|--|----------------------------|----------------------|
| Dixon Wax Crayon, Blue | Dry Cotton Cloth | 1 |
| Crayola, Water Based Marker Black | Dry Cotton Cloth | 1 |
| Sanford Sharpie, Solvent Based Blue | Citrus Clean Super 9800 | 3 |
| Avery, Permanent Marker Black | Citrus Clean Super 9800 | 3 |
| Krylon, Solvent Based Spray Paint Red | Citrus Clean Super 9800 | 3 |

cleanability levels 1-5 are defined as:

- Level 1: Graffiti completely removed with dry cotton cloth.
- Level 2: Graffiti completely removed with commercial aqueous detergent.
- Level 3: Graffiti completely removed with Citrus Clean Super 9800.
- Level 4: Graffiti completely removed with industrial cleaner/isopropanol
- Level 5: Graffiti completely removed with MEK

Requirements for ASTM D6578 Performance

| Property | Test Method | Requirement | Obtained |
|--------------------------|--------------------------|--|-------------|
| Graffiti Resistance | ASTM D6578 | Cleanability Level 8, 9 or 10 | 1-3 |
| Recleanability | ASTM D6578 | Minimum 10 Cycles | 200+ Cycles |
| Fluid Resistance | ASTM D 1308 ¹ | No Blistering, Discoloration, Softening or Adhesion Loss | Pass |
| Set-To-Touch Time | ASTM D1640 ² | 4-6 Hours | Pass |
| Dry-Thorough Time | ASTM D1640 ² | 24 Hours | Pass |
| Dry Hard | ASTM D1640 ² | 48 Hours | Pass |
| Complete Cure & Hardness | ASTM D1640 ² | 5-7 Days | Pass |

¹Spot Test using MEK

²3-Mil Wet Film Tested @77°F

WARRANTY INFORMATION: MONOPOLE believes that the information in this publication is an accurate description of the typical characteristics and/or uses of the product or products. But it is the end users responsibility to thoroughly test the product in the specific application to determine its performance efficacy and safety. Since use of this product is beyond our control, Monopole, Inc. cannot assume any risk or liability for results obtained when not used according to our specifications and directions. Unless MONOPOLE provides a specific written statement of fitness for a particular use, MONOPOLE'S sole warranty is that the product will meet its current sales specifications. MONOPOLE specifically disclaims any other expressed or implied warranty, including the warranty of merchantability and fitness for use. The exclusive remedy and MONOPOLE's sole liability for breach of warranty is limited to a refund of the purchase price or replacement of product proven to be defective. In no event shall the seller be liable for any loss of profits or other consequential damages. Under no circumstance will MONOPOLE pay labor charges.